

# Shatter Safe®

## Security Window Films

Toll Free: 1-888-948-8468

### Clear Shatter Safe® Security Films

STOCK #	Visible Light Transmittance (How much light comes through)	Total Solar Trans.	Total Solar Reflect	Total Solar Absorb	Visible Light Reflect	Winter U-Value	UV Rejected	Glare Reduce	Shading Coeffic.	Total Solar Energy Reject	Mils	Ply	Peel Strength (pi)	Tensile Strength (psi)
SSF-002	88%	75%	8%	17%	10%	1.05	99%	N/A	0.93	19%	2.0	1	5.0	25,000
SSF-003	86%	74%	8%	18%	10%	1.05	99%	N/A	0.92	20%	4.0	1	5.0	25,000
SSF-007	85%	71%	10%	19%	10%	1.05	99%	N/A	0.91	20%	7.0	1	5.0	25,000
SSF-008	83%	77%	8%	15%	10%	1.05	99%	N/A	0.92	19%	8.0	2	5.0	25,000
SSF-012	82%	70%	10%	20%	10%	1.05	99%	N/A	0.91	22%	11.0	2	5.0	25,000
SSF-016	82%	70%	9%	21%	10%	1.05	99%	N/A	0.9	25%	14.0	2	5.0	25,000
SSF-022	79%	65%	12%	23%	12%	1.01	99%	N/A	0.88	27%	21.0	3	5.0	25,000

This data is provided for information purposes only and is not to be considered part of the basis of any bargain or transaction involving Shatter Safe Security Window Films nor the OEM products. The included data does not constitute a recommendation for, endorsement of, or certification of the product or material tested. makes no representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to this test data. Shatter Safe Security Window Films and the OEM products limited warranty should be carefully reviewed prior to purchasing any product. Extrapolation of data from the sample or samples relating to the batch or lot from which data was obtained may not correlate and should be interpreted accordingly with caution. Shatter Safe Security Window Films nor the OEM shall not be responsible for variations in quality, composition, appearance, performance, or other features of similar subject matter produced by persons or under conditions over which Shatter Safe Security Window films nor the OEM has no control.